



PRILLED SULPHUR

PRELIMINARY DATA SHEET

CHARACTERISTIC	METHOD	UNIT	SPECIFICATION	
			Min	Max
FREE SULPHUR	TE-LAB-PRO-08-0035 (SRUAN – 4 (KTI))	wt %	99.8	-
MOISTURE	TE-LAB-PRO-08-0036 (SRUAN – 4 (KTI))	ppm wt	-	500
ASH	TE-LAB-PRO-08-0037 (SRUAN – 4 (KTI))	wt %	-	0.1
ACIDITY as H ₂ SO ₄	TE-LAB-PRO-08-0039 (SRUAN – 4 (KTI))	wt %	NIL	-
ORGANIC MATTER	TE-LAB-PRO-08-0040 (SRUAN – 4 (KTI))	wt %	-	0.1
CHLORIDES as NaCl	TE-LAB-PRO-08-0041 (SRUAN – 4 (KTI))	wt %	NIL	-
COLOR	TE-LAB-PRO-08-0043 (SRUAN – 4 (KTI))	VISUAL	Bright Yellow	-
BULK DENSITY (Loose)	TE-LAB-PRO-08-0045	Kg/m ³	1040	-
<u>SHAPE AND SIZE:</u>	TE-LAB-PRO-08-0044	mm	2.0	6.0
Retained on 6.3 mm	TE-LAB-PRO-08-0044	wt %	-	< 5.0
Pass thru 5.6 mm	TE-LAB-PRO-08-0044	wt %	75	-
Retained on 2.8 mm	TE-LAB-PRO-08-0044	wt %	75	-
Pass thru 1.0 mm	TE-LAB-PRO-08-0044	wt %	-	< 2.0
Pass thru 0.3 mm	TE-LAB-PRO-08-0044	wt %	-	< 0.5

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions, which may be encountered in the use thereof. Such questions should be investigated by those using this information. Q-Chem assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.

For more information:

Qatar Chemical Company LTD (Q-Chem)
P.O. Box 24646
Doha - Qatar
Tel: (+974) 4847110
(+974) 4847111
Email: marketing@qchem.com.qa
MSDS (+974) 4847110
OR
Visit our site
www.qchem.com.qa

Jan 2004